



Tel: 01384 354354
Fax: 01384 293086
info@grpbuildingproducts.co.uk
www.grpbuildingproducts.co.uk

Specification sheet for glass reinforced plastic products

All materials produced using:

Class E Chopped Strand Mat @ 450gm per ply
Minimum 2 ply on products
Mat tested to ISO 3374, 3344, 1887, 3342, 5025

Polyester Resins

Class 1 resin tested to BS476 part 7 – Flame surface spread
1.4g/cc Cured Density
0.2-0.3 Coefficient of Conductivity

Typical Values

Values are based on an absolute minimum of 2.46mm cross section

Weight per M2: 7kg m/2

R value: 0.012

Tested to UV Exposure @ 50°C and 10 year weathering Cycle – ISO 4892

Electromagnetic Shielding Effectiveness tested between 0 – 2500 Mhz: -0.2dB

Effective Peak @ 1700 Mhz: +0.6dB

BRE wind speed accreditation to BS6399 Part 2: Nominal Wind load pass @ +50 m/s or 112mph